



LEADING MANUFACTURER & MASTER DISTRIBUTOR

**NATIONAL
BRONZE &
METALS, INC.**



To Our Valued Customers:

Enclosed for your reference is a Material Safety Data Sheet (MSDS) for our major product lines. It has been prepared to comply with the Federal Hazard Communication Standard, 29 CFR 1910.1200. This MSDS contains important safety, health and regulatory information that is important to you, your employees and customers who are exposed to these materials. The MSDS is supplied to provide safety, health and environmental information only and must not be used for material specifications.

Please contact your sales person or call us directly if you require further assistance.

Sincerely,

NATIONAL BRONZE & METALS, INC.

**IMPORTANT
Liability Disclaimer**

The information contained in the attached Material Safety Data Sheet (MSDS) is believed to be correct as it was obtained from sources we believe are reliable. However, no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications, hazards connected with the use of the material, variations in methods, conditions and equipment used to store, handle, or process the material and hazards connected with the use of the material are solely the responsibility of the user and remain at his sole discretion.

Compliance with all applicable federal, state, and local laws and regulations remains the responsibility of the user, and the user has the responsibility to provide a safe work place to examine all aspects of its operation and to determine if or where precautions, in addition to those described herein, are required.

MATERIAL SAFETY DATA SHEET

National Bronze & Metals, Inc.

2929 West 12th
Houston, Texas 77008
Telephone: 713-869-9600 Fax: 713-869-9124

Date: Dec. 17, 2008
Revised: 08/28/2012

Section I Material Identification

Copper Base Alloys

See alloy composition sheets for alloy presence and percentages of alloying ingredients.

Section II Hazardous Ingredients

Copper Base Alloys

	CAS Number	PEL Dust	PEL FUME	TLV DUST	TLV FUME	ACGIH STEL DUST	ACGIH STEL FUME
Aluminum	(7429-90-5)	15 mg/m ³	5 mg/m ³	10 mg/m ³	5 mg/m ³		
Arsenic	(7440-38-2)	.01 mg/m ³		.02 mg/m ³			
Antimony	(7440-36-0)	0.5 mg/ m ³		0.5 mg/ m ³			
Beryllium	(7440-41-7)	.002 mg/m ³		.002 mg/m ³		.005 mg/m ³	
Bismuth Telluride	(1304-82-1)	15 mg/ m ³		15 mg/ m ³			
Carbon	(7440-44-0)	15 mg/m ³	5 mg/m ³	10 mg/m ³			
Chromium	(7440-47-3)	1 mg/m ³		.5 mg/m ³			
Cobalt	(7440-48-4)	.05 mg/m ³		.05 mg/m ³			
Columbium	(7440-03-1)	15 mg/m ³		10 mg/m ³			
Copper	(7440-50-8)	1 mg/m ³	.1 mg/m ³	1 g	.2 mg/m ³		
Iron	(1309-37-1)	10 mg/m ³		5 mg/m ³			
Lead	(7439-92-1)	.05 mg/m ³		.05 mg/m ³			
Manganese	(7439-96-5)	5 mg/m ³		.20 mg/m ³	1 mg/m ³		3 mg/m ³
Magnesium	(7439-95-4)	15 mg/m ³		10 mg/m ³			
Molybdenum	(7439-98-7)	10 mg/m ³		10 mg/m ³			
Nickel	(7440-02-0)	1 mg/m ³	1 mg/m ³	.05 mg/m ³	.05 mg/m ³		
Phosphorous	(7723-14-0)	.1 mg/m ³		.1 mg/m ³			
Silicon	(7440-21-3)	15 mg/m ³	5 mg/m ³	*10 mg/m ³			
Silver	(7440-22-4)	.01 mg/m ³		.1 mg/m ³			
Sulphur	(7446-09-5)	15 mg/m ³		10 mg/m ³		5 mg/m ³	
Tungsten	(7440-33-7)	5 mg/m ³		5 mg/m ³			
Titanium	(7440-32-6)						
Tantalum	(7440-25-7)	5 mg/m ³		5 mg/m ³			
Tellurium	(13494-80-9)	.01 mg/m ³		.01 mg/m ³			
Tin	(7440-31-5)	2 mg/m ³		2 mg/m ³			
Vanadium	(7440-62-2)	.05 mg/m ³	.1 mg/m ³	.05 mg/m ³	.05 mg/m ³		
Yttrium Oxide	(1314-36-9)	1 mg/m ³		1 mg/m ³			
Zinc	(7440-66-6)	10 mg/m ³	5 mg/m ³	10 mg/m ³	5 mg/m ³	10 mg/m ³	

*Value is for the total dust containing no asbestos and less than 1% free silicon.

Note: Antimony trioxide, beryllium, cadmium, chromium, cobalt-chromium alloy, lead and nickel have been identified as potential human carcinogens. # denotes a toxic chemical or chemicals subject to reporting requirements of subject to reporting requirements of section 313 of Title III of the S.A.R.A. of 1986 and CFR Part 372.

NATIONAL BRONZE & METALS, INC.

PO BOX 800818, HOUSTON, TEXAS 77280 | (P) 713.869.9600 | (F) 713.869.9124 | (E) SALES@NBMMETALS.COM | NBMMETALS.COM

Section III Physical Data Physical Form Solid Odor: None

	Aluminum	Copper	Lead	Steel	Nickel
Specific Gravity (H2O = 1)	2.5+	7.5+	8+	7+	8-9
Melting Point (C)	480+	1,000+	180+	1,300+	>1,400
Color	Silver	Yellow Red	Soft Gray	Gray-Black	Silver
Solubility in H2O	None	None	None	None	None

Section IV Fire and Explosion Data

Flash Point: (Method Used) Not Applicable

Extinguishing Media: See Below

Flammable Limits (LEL-UEL): Not Applicable

Auto Ignition Temp.: Not Applicable.

Special Fire Fighting Procedures: Solid massive form is not combustible. Fire and explosion hazards are moderate when material is in the form of dust and exposed to heat, flames, chemical reaction, or in contact with powerful oxidizers.

Use special mixtures of dry chemical or sand. Firefighters should wear self-contained breathing apparatus and protective clothing.

Section V. Reactivity Data

Stability: Stable

Conditions to Avoid: Stable under normal conditions of transport and storage. Molten metal may react violently with water.

Incompatibility (Materials to Avoid): Acids, Bases, and oxidizers.

Hazardous Decomposition or By Products: Metal Fumes

Hazardous Polymerization: Will not occur.

Section VI Heath Hazard Data

Permissible exposure Limits and threshold limit values: See Section II

Route(s) of Entry: Inhalation: Yes; **Skin:** Yes **Indigestion:** Yes

Under normal handling conditions the sold alloy presents no significant heath hazards. Processing of the alloy by dust or fume producing operation (grinding, buffing, heating, welding, ect.) may result in the potential for exposure to airborne metal particulates or fume. The exposure levels in Section II are relevant to fumes and dust.

Effect of Overexposure:

Aluminum: Excessive exposure to aluminum fumes or dust has been associated with lung disease, but this effect is probably due to simultaneous silica exposure.

Antimony: Antimony and its compounds are irritating to the skin and mucous membranes and are systemic poisons. Effects are reported to include metallic taste in mouth, vomiting, colic, loss of appetite and weight, cardiac problems, and diarrhea. In addition, dermatitis may result which starts as an inflammation of the hair follicles and can progress through pus formation and sloughing to leave a contracted scar. Damage to the lungs may be in both acute and chronic forms, both of which have similar signs and symptoms. These include a relatively non-productive cough, progressive difficulty in breathing, loss of appetite, and loss of weight. The major difference between the two is the suddenness of onset and the rate of progression. In the acute form, the symptoms appear in several hours to several weeks after exposure and there is usually rapid progression of signs including dyspnea, anorexia, and extreme weight loss. Complete recovery is possible and fatal cases usually result from acute heart disease. In chronic beryllium disease, the symptoms or signs are generally delayed in their onset and are persistent in nature. They may be triggered or aggravated by stress such as pregnancy, respiratory infection, and thyrotoxicosis. In the progression of the disease, symptoms of heart disease may occur.

Arsenic: Arsenic compounds can be absorbed into the body from industrial exposures, especially by inhalation and ingestion. Signs of Toxicity are dermal lesions, conjunctivitis, upper respiratory tract irritation, nausea, vomiting, peripheral neuritis and occasionally anemia. Arsenic in combination with promoters such as sulfur dioxide, metal oxide fumes and smoking has caused respiratory cancer. Arsenic has been identified as a carcinogen by NTP and IARC.

Beryllium: Inhalation of Beryllium dust or fume may result in the production of an acute or chronic systemic disease depending upon the level of exposure and the beryllium compound involved. Granulomatous lesions of the skin, liver, kidneys, spleen and lymph nodes have been reported. Damage to the lungs may be in both the acute and chronic forms, both of which have similar signs and symptoms. These include a relatively non-productive cough, progressive difficulty in breathing, loss of appetite, and loss of weight. The major difference between the two is the suddenness of onset and rate of progression. In the acute form, the symptoms appear in several hours to several weeks after exposure and there is usually rapid progression of signs including dyspnea, anorexia, and extreme weight loss. Complete recovery is possible and fatal cases usually result from acute heart disease. In chronic beryllium disease, the symptoms or signs are generally delayed in their onset and are persistent in nature. They may be triggered or aggravated by stresses such as pregnancy, respiratory infection and thyrotoxicosis. In the progression of the disease, symptoms of heart disease may occur. Beryllium is also a suspected human carcinogen and has caused cancer in laboratory animals.

Cadmium: Inhalation of cadmium fumes may cause respiratory irritation with sores, dry throat and a metallic taste followed by a cough, chest pain and difficulty in breathing. Bronchitis, pneumonitis, and pulmonary edema have been reported because of the irritation of fumes. Headaches, dizziness, loss of appetite, and weight loss have been reported and the liver, kidneys and bone marrow may be injured by the presence of the metal. Continued exposure to low levels of cadmium has resulted in chronic poisoning characterized by irreversible lung damage and kidney damage. A single, high-level exposure to cadmium can cause severe lung irritation, which may be fatal. Cadmium is also a suspected human carcinogen.

Chromium: In some workers, chromium compounds act as allergens, may cause dermatitis, and may produce pulmonary sensitization. Chronic acid and chromates have a direct corrosive effect on the skin and mucous membranes of the upper respiratory tract. Although rare, there may be the possibility of skin and pulmonary sensitization. IARC has determined that there is sufficient evidence of increase lung cancer among workers in the chromate-producing industry and possibly among chromium alloy workers. This determination is supported by sufficient evidence for carcinogenicity to animals and possibly mutagenicity testing of CR VI compounds.

Cobalt: Cobalt has been reported as causing hyper sensitization-type dermatitis in individuals who are susceptible. Animal studies have shown that particulate cobalt is an acutely irritating substance and industrial exposures, possibly combined with small amounts of silica, are reported capable of producing serious pneumoconiosis which is initially of an insidious nature.

Columbium: Also known as niobium, there is almost no information on the toxicity of this metal or its fumes. Russian medical literature has described early chest X-Ray changes in welders and chemical workers handling niobium and tantalum, but no specific data has been found. It is expected that the metal dust and fumes could cause irritation to the skin, eyes, and respiratory tract upon acute exposure.

Copper: Melting, grinding or cutting of copper may produce fumes or dust. Exposure to, or inhalation of these fumes may present potentially significant health hazards. Fumes of copper may cause metal fume fever with flu-like symptoms and skin and hair discoloration. While industrial dermatitis has not been reported, keratinization of the hands and soles of the feet has been reported. Systemically as well, copper dust and fumes cause irritation of the upper tract, metallic taste in the mouth, and nausea.

Iron: The inhalation of iron oxide fumes or dust may cause an apparent benign pneumoconiosis, which is called siderosis. This disease is reported to be disabling, but makes X-Ray diagnosis of other lung conditions difficult or impossible.

Lead Short Term exposure: Lead is an accumulative poison. The effects of inhalation of fumes or dust of inorganic lead may not develop quickly. Symptoms may include decreased physical fitness, fatigue, sleep disturbance, headache, aching bones and muscles, constipation, abdominal pains and decreased appetite. The effects are reversible and complete recovery is possible. Inhalation of large amounts of lead may lead to seizures, coma and even death.

Lead Long Term Exposure: Long term exposure can result in a build-up of lead in the body and more severe symptoms. These include anemia, pale skin, a blue line at the gum margin, decreased hand-grip strength, abdominal pain, severe constipation, nausea, vomiting and paralysis of the wrist joint. Prolonged exposure may also result in kidney damage. If the nervous system is affected, usually due to very high exposures, the resulting effects include severe headaches, convulsions, coma, delirium and death. Alcohol ingestion and physical exertion may bring on symptoms. Continued exposure can result in decreased fertility and/or increased chance of miscarriages or birth defects.

Magnesium: Exposure to magnesium may cause metal fume fever with flu- like symptoms. Particles imbedded in the skin may cause severe lesions.

Manganese: Chronic manganese poisoning may result from inhalation of dust or fumes. The central nervous symptom is the chief site of injury, but there may also be adverse blood and kidney effects. Chronic manganese poisoning is not a fatal disease although it is extremely disabling. Some individuals may be hyper-susceptible to manganese. Freshly formed manganese fumes have caused fever and chills similar to metal fumes fever.

Molybdenum: This metal can be toxic via intraperitoneal and subcutaneous routes. Care should be taken to avoid inhalation of large amounts of dust or fumes. Molybdenum is generally considered to exhibit a low order of toxicity.

Nickel: The most common ailment arising from nickel or its compounds is an allergic dermatitis known as "nickel-itch" which usually occurs when the skin is moist. Generally, nickel and most salts of nickel do not cause systemic poisoning, but nickel has been identified as a suspected carcinogen. There can also be adverse effects to the lungs and nasal cavities.

Phosphorus: The dust and fumes can act as minor irritants to the eyes, throat, and respiratory tract. Long-term excessive inhalation of phosphorus compounds may lead to cough, bronchitis and pneumonia.

Silicon: Accumulation of silicon in the lungs may be responsible for benign pneumoconiosis, but is not considered to be responsible for pulmonary functional impairment or respiratory symptoms.

Silver: Chronic occupational exposure to silver results in argyria, a permanent pigmentation, (gray to purple) of the skin and eyes. Inhalation of silver may localize the argyria in the respiratory tract with chronic bronchitis as the only symptom.

Sulfur: In fumes may irritate: skin, eyes, lungs and gastrointestinal tract.

Tantalum: There are no reports of adverse health effects in industrially exposed workers. Massive doses of tantalum given by the intratracheal route to rats have produced respiratory tract lesions. In contact with tissue, metallic tantalum is inert. Tantalum pentoxide has an LD of > 8 g/kg, orally in rats.

Tellurium: Inhalation of tellurium fumes in quantities results in a metallic taste and garlic breath, gastrointestinal disease, dry mouth and somnolence.

Tin: The inhalation of tin fumes or dust may cause an apparent benign pneumoconiosis called stannosis which is reported to be not disabling.

Titanium: Titanium is considered a physiologically inert dust. However, high concentrations of oxides can cause mechanical irritation of eyes, nose and throat. Inhalation of titanium dioxide dust or fume could produce lung fibrosis and chronic bronchitis.

Tungsten: Inhalation of tungsten dust may cause irritation of the respiratory tract. Skin or eye contact could cause abrasion or irritation of the respective surfaces. No hazards have been identified for tungsten fume except that it may aggravate an existing chronic respiratory disease.

Yttrium Oxide: Short term inhalation in large amounts could cause discomfort, coughing and nasal discharge similar to the symptoms of a bad cold. Drying of the mucous membranes might be experienced. After intratracheal administration in rats, emphysema and diffused modular fibrosis in the lungs have been reported. The oral toxicity of this material is low as it is poorly absorbed from the gastrointestinal tract. Skin and eye contact should produce no problems other than mechanical irritation.

Zinc: (as Oxide): Zinc is very low in toxicity, but inhalation of fumes may cause metal fume fever. Onset of symptoms may be delayed 4 to 12 hours and include irritation of the nose, mouth and throat, coughing, stomach pain, headache, nausea, vomiting, metallic taste, chills, fever, pains in the muscles and joints, thirst, bronchitis or pneumonia and a bluish tint to the skin. These symptoms go away in 24 to 48 hours and leave no effect.

Note: Antimony trioxide, beryllium, cadmium, chromium, cobalt-chromium alloy, lead and nickel have been identified as potential human carcinogens.

Emergency First Aid Procedures:

Eye Contact – Flush well with running water to remove particulate. Obtain medical attention.

Skin Contact – vacuum off excess dust. Wash well with soap and water.

Inhalation – Remove individual to fresh air. Obtain medical attention.

Ingestion – Seek medical attention if large quantities of materials have been ingested.

SECTION VII. PRECAUTIONS FOR SAFE HANDLING OR USE

Steps to be taken in case material is released or spilled:

No special precautions are necessary for spills of bulk material. If large quantities of dust are spilled, remove by vacuuming or wet-sweeping to prevent heavy concentration of airborne dust. If liquids (acids or bases) containing solubilized metal are spilled, evacuate unprotected personnel from the area. Absorb liquid by use of vermiculite, dry sand or similar material. Follow federal, state and local regulations. Clean-up personnel should wear respirators and protective clothing. Ventilate the area where the release occurred.

Precautions to be Taken in Handling and Storage:

Store materials away from incompatible materials and keep dust from sources of ignition.

Other Precautions:

See all other sections of this MSDS.

SECTION VIII. CONTROL MEASURES

Respiratory Protection: If exposure is above the PEL or TLV, use a NIOSH-approved respirator for fume or dust, dependent upon the source of airborne contaminant.

Ventilation: Ventilation is required if dust or fume is created in the handling of, or the working on of this material.

Local Exhaust: This is required if dust or fume is created in the handling of, or the working on of this material.

Mechanical (general): Control as above to reduce airborne dust or fume levels.

Protective Gloves: These gloves are required for melt, grind, cut or weld operations. Select a glove approved for the specific operation.

Eye Protection: Protection is required for melt, grind, cut or weld operations. There is minimum requirement of safety glasses with side shields for these operations. Melting and welding may require special eye protection including face shields and specially tinted lass. Grinding operations may also require face shields.

Other Protective Clothing or Equipment: Other protection or equipment may be required depending upon the work being done on or with the material.

Work/Hygiene Practices: Observe practices required for work done with lead-bearing materials to meet requirements of the OSHA lead standard where necessary. Always evaluate the jobs done on this product in accordance with OSHA or relevant federal, state or local standards.

IMPORTANT LIABILITY DISCLAIMER

The information contained in this Material Safety Data Sheet (MSDS) is believed to be correct as it was obtained from sources which we believe are reliable, including: "Threshold Limit Values & Biological Exposure Indices for 1988-89" (American Conference of Government & Industrial Hygienists), Air Contaminants, Permissible Exposure Limits (Title 29, Code of Federal Regulations, part 1920, 1000 – OSHA), and OSHA (Cleveland Area Office) letter of 6/15/89. However, no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications, hazards connected with the use of the material, or the results to be obtained from the use thereof. User assumes all risks and liability of any use, processing or handling of any material, variations in methods, conditions and equipment used to store, handle or process the material and hazards connected with the use of the material are solely the responsibility of the user and remain at his sole discretion.

Compliance with all applicable federal, state and local laws and regulations remains the responsibility of the user, and the user has the responsibility to provide a safe work place, to examine all aspects of its operations and to determine if or where precautions, in addition to those described herein, are required.

Note: Chemical analysis has not been performed by **NBM**. Data supplied is furnished by various suppliers. For actual compositions, please refer to "Certified Material Test Report" or specific grade specification sheets.

The information contained in these alloy composition sheets should not be used for ordering or specification purposes. It is only intended to give general information for Material Data Sheets purposes.

COPPER ALLOYS (% max., unless shown as range or min.)	Aluminum-Al	Antimony-Sb	Arsenic-As	Beryllium-Be	Cadmium-Cd	Cobalt-Co	Copper, incl. Silver- Cu/Ag	Chromium-Cr	Iron-Fe	Lead-Pb	Manganese-Mn	Nickel, incl. Cobalt- Ni/Co	Phosphorus-P	Silicon-Si	Sulfur-S	Tellurium-Te	Tin-Sn	Zinc-Zn	Zirconium-Zr
	10100		0.0004	0.0005			99.99 Min	0.0001	0.0010	0.0005	0.00005	0.0010	0.0003				0.002	0.0001	
10200						99.95 Min													
11000						99.90 Min													
12000						99.90 Min						0.004-0.012							
12200						99.90 Min						0.015-0.040							
14500						99.90 Min						0.004-0.012			0.40-0.7				
15000						99.80 Min												0.10-0.20	
16200					0.7-1.2	Rem.		0.02											
16500					0.6-1.0	Rem.		0.02									0.50-0.7		
17200	0.20			1.80-2.00		Rem.					0.20 Min		0.2						
17300	0.2-0.6			1.80-2.00		Rem.			0.20-.6		0.20		0.2						
17510	0.20			0.2-0.6	0.30	Rem.		0.10			1.4-2.2		0.2						
18000						Rem.	0.10-0.8	0.15			1.8-3.0		.40-.8						
18150						Rem.	0.50-1.5											0.05-0.25	
18200						Rem.	0.6-1.2	0.10	0.05										
18700						99.5 Min			0.8-1.5										
19140						Rem.		0.05	0.40-.8		0.8-1.2	0.15-0.35				0.05	0.5		
19160						Rem.		0.05	0.8-1.2		0.8-1.2	0.15-0.35				0.05	0.50		
21000						94.0-96.0		0.05	0.05									Rem.	
22000						89.0-91.0		0.05	0.05									Rem.	
22600						86.0-89.0		0.05	0.05									Rem.	
23000						84.0-86.0		0.05	0.05									Rem.	
23400						81.0-84.0		0.05	0.05									Rem.	
24000						78.5-81.5		0.05	0.05									Rem.	
26000						68.5-71.5		0.05	0.07									Rem.	
27000						63.0-68.5		0.07	0.10									Rem.	
27200						62.0-65.0		0.07	0.07									Rem.	
27400						61.0-64.0		0.05	0.10									Rem.	
28000						59.0-63.0		0.07	0.30									Rem.	
31400						87.5-90.5		0.10	1.3-2.5		0.7							Rem.	
31600						87.5-90.5		0.10	1.3-2.5		0.7-1.2	0.04-0.10						Rem.	
34500						62.0-65.0		0.15	1.5-2.5									Rem.	
35300						61.0-63.0		0.15	1.5-2.5									Rem.	
36000						60.0-63.0		0.35	2.5-3.7									Rem.	
37700						58.0-61.0		0.30	1.5-2.5									Rem.	
38000	0.50					55.0-60.0		0.35	1.5-2.5							0.3		Rem.	
38500						55.0-59.0		0.35	2.5-3.5									Rem.	
44300						70.0-73.0		0.06	0.07								0.9-1.2	Rem.	
46200						62.0-65.0		0.10	0.20								0.50-1.0	Rem.	
46400						59.0-62.0		0.10	0.20								0.50-1.0	Rem.	
48200						59.0-62.0		0.10	0.40-1.0								0.50-1.0	Rem.	
48500						59.0-62.0		0.10	1.3-2.2								0.50-1.0	Rem.	

COPPER ALLOYS (%max., unless shown as range or min.)	Copper Alloy Composition Limits																		
	Aluminum-Al	Antimony-Sb	Arsenic-As	Beryllium-Be	Cadmium-Cd	Cobalt-Co	Copper, incl. Silver-Cu/Ag	Chromium-Cr	Iron-Fe	Lead-Pb	Manganese-Mn	Nickel, incl. Cobalt-Ni/Co	Phosphorus-P	Silicon-Si	Sulfur-S	Tellurium-Te	Tin-Sn	Zinc-Zn	Zirconium-Zr
48600						59.0-62.0			1.0-2.5								0.30-1.5	Rem.	
50700			0.02-0.25			Rem.		0.10	0.05				0.30				1.5-2.0		
51000						Rem.		0.10	0.050				0.03-0.35				4.2-5.8	0.30	
52100						Rem.		0.10	0.050				0.03-0.35				7.0-9.0	0.20	
52400						Rem.		0.10	0.050				0.03-0.35				9.0-11.0	0.20	
53400						Rem.		0.10	.8-1.2				0.03-0.35				3.5-5.8	0.30	
54400						Rem.		0.10	3.5-4.5				0.01-0.50				3.5-4.5	1.5-4.5	
61000	6.0-8.5					Rem.		0.50	0.02				0.10					0.20	
61300	6.0-7.5					Rem.		2.0-3.0	0.01	0.20	0.15	0.015	0.10			0.20-0.50	0.10		
61400	6.0-8.0					Rem.		1.5-3.5	0.01	1.00		0.015						0.20	
61800	8.5-11.0					Rem.		0.50-1.5	0.02				0.10					0.02	
62300	8.5-10.0					Rem.		2.0-4.0		0.50	1.0		0.25			0.60			
62400	10.0-11.5					Rem.		2.0-4.5		0.30			0.25			0.20			
62500	12.5-13.5					Rem.		3.5-5.5		2.0									
63000	9.0-11.0					Rem.		2.0-4.0		1.50	4.0-5.5		0.25			0.20	0.30		
63020	10.0-11.0				0.20	74.5 Min	0.05	4.0-5.5	0.03	1.5	4.2-6.0					0.25	0.30		
63200	8.7-9.5					Rem.		3.5-4.3	0.02	1.2-2.0	4.0-4.8		0.10						
63400	2.6-3.2		0.09			Rem.		0.15	0.05		0.15		0.25-0.45			0.20	0.50		
63600	3.0-4.0		0.15			Rem.		0.15	0.05		0.15		0.7-1.3			0.20	0.50		
64200	6.3-7.6		0.15			Rem.		0.30	0.05	0.10	0.25		1.5-2.2			0.20	0.50		
64210	6.3-7.0		0.15			Rem.		0.30	0.05	0.10	0.25		1.5-2.0			0.20	0.50		
64700						Rem.		0.10	0.10		1.6-2.2		0.40-0.8				0.50		
65100						Rem.		0.8	0.05	0.7			0.8-2.0				1.5		
65300						Rem.		0.8	0.05				2.0-2.6						
65500						Rem.		0.8	0.05	0.50-1.3	0.6		2.8-3.8				1.5		
65600	0.01					Rem.		0.5	0.02	1.50			2.8-4.0			1.50	1.5		
65620						90.00 min		1.0-2.0		1.0		0.1	2.4-4.0				1.5-4.0		
67300	0.25					58.0-63.0		0.50	0.4-3.0	2.0-3.5	0.25		0.50-1.5			0.30	Rem.		
67310	0.25					58.25-62.0		0.35	0.50-1.75	2.0-3.5	0.25		0.50-1.5			0.30	Rem.		
67400	0.50-2.0					57.0-60.0		0.35	0.50	2.0-3.5	0.25		0.50-1.5			0.30	Rem.		
67410	1.3-2.3					55.5-59.0		1.0	0.80	1.0-2.4	2.0		0.7-1.3			0.5	Rem.		
67420	1.0-2.0					57.0-58.5		.15-.55	0.25-0.8	1.5-2.5	0.25		0.25-0.7			0.35	Rem.		
67500	0.25					57.0-60.0		0.8-2.0	0.20	0.05-0.50						0.50-1.5	Rem.		
67600						57.0-60.0		0.40-1.3	0.50-1.0	0.05-0.50						0.50-1.5	Rem.		
68700	1.8-2.5		0.02-0.06			76.0-79.0		0.06	0.07								Rem.		
69430			0.03-0.06			80.0-83.0		0.20	0.30				3.5-4.5				Rem.		
70600						Rem.		1.0-1.8	0.05	1.0	9.0-11.0						1.0		
71500						Rem.		0.40-1.0	0.05	1.0	29.0-33.0						1.0		
75200						63.0-66.5		0.25	0.05	0.50	16.5-19.5						Rem.		
79200						59.0-66.5		0.25	0.8-1.4	0.50	11.0-13.0						Rem.		
79800						45.5-48.5		0.25	1.5-2.5	1.5-2.5	9.0-11.0						Rem.		
83600		0.25				84.0-86.0			4.0-6.0		1.0					4.0-6.0	4.0-6.0		

COPPER ALLOYS

(%max., unless shown as range or min.)

	<i>Aluminum-Al</i>	<i>Antimony-Sb</i>	<i>Arsenic-As</i>	<i>Beryllium-Be</i>	<i>Cadmium-Cd</i>	<i>Cobalt-Co</i>	<i>Copper, incl Silver-Cu/Ag</i>	<i>Chromium-Cr</i>	<i>Iron-Fe</i>	<i>Lead-Pb</i>	<i>Manganese-Mn</i>	<i>Nickel, incl Cobalt-Ni/Co</i>	<i>Phosphorus-P</i>	<i>Silicon-Si</i>	<i>Sulfur-S</i>	<i>Tellurium-Te</i>	<i>Tin-Sn</i>	<i>Zinc-Zn</i>	<i>Zirconium-Zr</i>		
84400	0.005	0.25					78.0-82.0	0.40	6.0-8.0		1.0	1.5	0.005	0.08			2.3-3.5	7.0-10.0			
86200	3.0-4.9						60.0-66.0	2.0-4.0	0.20	2.5-5.0	1.0						0.20	22.0-28.0			
86300	5.0-7.5						60.0-66.0	2.0-4.0	0.20	2.5-5.0	1.0						0.20	22.0-28.0			
86400	0.50-1.5						56.0-62.0	0.40-2.0	0.50-1.5	0.1-1.5	1.0						0.50-1.5	34.0-42.0			
86500	0.50-1.5						55.0-60.0	0.40-2.0	0.40	0.10-1.5	1.0						1.0	36.0-42.0			
90200	0.005	0.20					91.0-94.0	0.20	0.30		0.5	0.05	0.005	0.05			6.0-8.0	0.5			
90300	0.005	0.20					86.0-89.0		0.30		1.0	1.5	0.005	0.05			7.5-9.0	3.0-5.0			
90500	0.005	0.20					86.0-89.0	0.20	0.30		1.0	1.5	0.005	0.05			9.0-11.0	1.0-3.0			
90700	0.005	0.20					88.0-90.0	0.15	0.50		0.50	1.5	0.005	0.05			10.0-12.0	0.50			
91000	0.005	0.20					84.0-86.0	0.10	0.20		0.80	1.5	0.005	0.05			14.0-16.0	1.50			
91100	0.005	0.20					82.0-85.0	0.25	0.25		0.50	1.0	0.005	0.05			15.0-17.0	0.25			
91700	0.005	0.10					84.0-87.0	0.2	0.25		1.2-2.0	0.30	0.005	0.05			11.3-12.5	0.25			
92200	0.005	0.25					86.0-90.0	0.25	1.0-2.0		1.0	1.5	0.005	0.05			5.5-6.5	3.0-5.0			
92300	0.005	0.25					85.0-89.0	0.25	0.30-1.0		1.0	1.5	0.005	0.05			7.5-9.0	2.5-5.0			
92500	0.005	0.25					85.0-88.0	0.3	1.0-1.5		0.8-1.5	1.5	0.005	0.05			10.0-12.0	0.50			
92600	0.005	0.25					86.0-88.5	0.2	8-1.5		0.7	0.03	0.005	0.05			9.3-10.5	1.3-2.5			
92700	0.005	0.25					86.0-89.0	0.2	1.0-2.5		1	1.5	0.005	0.05			9.0-11.0	0.7			
92800	0.005	0.25					78.0-82.0	0.2	4.0-6.0		0.8	1.5	0.005	0.05			15.0-17.0	0.8			
92900	0.005	0.25					82.0-86.0	0.2	2.0-3.2		2.8-4.0	1.5	0.005	0.05			9.0-11.0	0.25			
93200	0.005	0.35					81.0-85.0	0.20	6.0-8.0		1.0	1.5	0.005	0.08			6.3-7.5	2.0-4.0			
93400	0.005	0.50					82.0-85.0	0.20	7.0-9.0		1.0	1.5	0.005	0.08			7.0-9.0	0.8			
93600	0.005	0.55					79.0-83.0	0.20	11.0-13.0		1.0	1.5	0.005	0.08			6.0-8.0	1.0			
93700	0.005	0.50					78.0-82.0	0.7	8.0-11.0		0.50	1.5	0.005	0.08			9.0-11.0	0.8			
93800	0.005	0.80					75.0-79.0	0.15	13.0-16.0		1.0	1.5	0.005	0.08			6.3-7.5	0.8			
94100	0.005	0.80					72.0-79.0	0.25	18.0-22.0		1.0	1.5	0.005	0.08			4.5-6.5	1.0			
94300	0.005	0.80					67.0-72.0	0.15	23.0-27.0		1.0	1.5	0.005	0.08			4.5-6.0	0.8			
94500	0.005	0.80					Rem.	0.15	16.0-22.0		1.0	1.5	0.005	0.08			6.0-8.0	1.2			
94700	0.005	0.15					85.0-90.0	0.25	0.09	0.2	4.5-6.0	0.05	0.005	0.05			4.5-6.0	1.0-2.5			
94800	0.005	0.15					84.0-89.0	0.25	3.0-1.0	0.2	4.5-6.0	0.05	0.005	0.05			4.5-6.0	1.0-2.5			
95200	8.5-9.5						86.0 Min	2.5-4.0													
95300	9.0-11.0						86.0 Min	0.8-1.5													
95400	10.0-11.5						83.0 Min	3.0-5.0		0.50	1.5										
95500	10.0-11.5						78.0 Min	3.0-5.0			3.5	3.0-5.5									
95510	9.7-10.9						78.0 Min	2.0-3.5			1.5	4.5-5.5					0.20	0.3			
95520	10.5-11.5				0.20		74.5 Min	0.05	4.0-5.5	0.03	1.5	4.2-6.0		0.15			0.25	0.3			
95800	8.5-9.5						79.0 Min	3.5-4.5	0.03	0.8-1.5	4.0-5.0		0.1								
95900	12.0-13.5						Rem.	3.0-5.0		1.5	0.5										
96900							Rem.	0.5	0.02	0.5-3.0	14.5-15.5						7.5-8.5	0.5			
97600	0.005	0.25					63.0-67.0	1.5	3.0-5.0	1.0	19.0-21.5	0.05	0.15	0.08			3.5-4.5	3.0-9.0			
97800	0.005	0.20					64.0-67.0	1.5	1.0-2.5	1.0	24.0-27.0	0.05	0.15	0.08			4.0-5.5	1.0-4.0			
99350	10.7-11.5				1-2		Rem.	.4 - 1.0	.02		13.5-16.5		.02				.05				
99500	0.50-2.0						Rem.	3.0-5.0	0.25	0.50	3.5-5.50		0.50-2.0						0.50-2.0		
99700	0.50-3.0						54.0 Min	1.0	2.0	11.0-15.0	4.0-6.0						1.0	19.0-25.0			
NBM37	15.0						79.5	5.0													
UZ19AL6	6.5-7.0						79.5	3.5		4.5-5.5									18-21		
SAE 841							87.5-90.5	1.0										9.5-10.5			